



IJEAST

INTERNATIONAL JOURNAL
OF ENGINEERING APPLIED SCIENCE
AND TECHNOLOGY



VOLUME : 4 ISSUE : 07 Print / Issue Publication Date: 07-Jan-2020



ISSN : 2455-2143



DOI : 10.33564/IJEAST.2019.v04i07.045

Indexed In



WWW.IJEAST.COM

editor@ijeast.com



NON CONVENTIONAL SOLVOTHERMAL-ASSISTED SYNTHESIS OF NANO LEAD(II) SULFIDE FROM DITHIOCARBAMATE PRECURSOR BIS (N-PHENYL-1- NAPHTHYLDITHIOCARBAMATE) - CHARACTERIZATION

S. Srinivasan

Department of Chemistry, Annamalai University Deputed to Arignar Anna Govt. Arts College
Vadachennimalai Attur Salem(Dt), Tamilnadu, India

Abstract - A non conventional solvothermal formation of PbS nano particles is reported with nickel dithiocarbamate as single source precursor. Morphology and composition of the nano product have been characterized by PXRD, SEM and EDX analysis. The precursor complex $[Pb(pndtc)_2]$ (where $pndtc = n$ -phenyl-1-naphthyl dithiocarbamate) are synthesized and characterized by elemental analysis, electronic, IR spectral, 1H and ^{13}C NMR spectroscopy. Electronic spectral band of compound show bands at 435 nm due to charge transfer. For complex the ν_{C-N} band is observed at 1499 cm^{-1} in IR. In the ^{13}C NMR spectra of the complexes the thioureide ($N^{13}CS_2$) carbons resonate at 206.6 ppm. 1H NMR showed the observed deshielding of the $-CH_2$ protons in the compound is attributed to the shift of electron density on the sulfur (or the metal) through the thioureide π system.

Keywords: dithiocarbamate, thioureide, solvothermal formation, scanning electron micrograph, powder diffraction.

I. INTRODUCTION

Metal dithiolates are used as single source precursors for metal sulphides. Various iron, cobalt and nickel 1,1 dithiolates have been investigated as precursors in metal organic chemical vapour deposition [1-3]. The variety of dithiocarbamate bis (N-alkyl dithiocarbamate) nickel(II) complexes, $[Ni(S_2CNH(n-pr)_2)]$,

$[Ni(S_2CNH(ipr')_2)]$ [4], $[Zn(S_2CN(C_2H_5)_2)_2]$ [5,6], $M[(S_2CN(C_2H_5)_2)_2]$ ($M=Pb, Cd$) [7], $Pb[(S_2CN(Bu_2'')_2)]$ [8], $Cr[(S_2CN(C_2H_5)_2)_3]$ [9] and $Cu[(S_2CN(Pr_2)_2)]$ [10] have been used as single source precursors for the production of thin layers of metal sulphides, viz., NiS , ZnS , PbS , CdS , Cr_2S_3 and Cu_2S respectively by chemical vapour deposition method. Solvothermal synthesis has been used to produce nano structured products titanium dioxide [11], graphene [12], carbon sphere [13], chalcogenide [14] and other products. Synthesis of high quality CdS nano rods by solvothermal process and their photoluminescence has been reported [15]. The obtained product was investigated by PXRD, HRTEM, FE-SEM, UV-Vis spectrum and photoluminescence. Shape controlled synthesis of PbS microcrystals in large yields via a solvothermal synthesis [16]. A simple and facile solvothermal synthesis of Hierarchical PbS microstars with multidendritic arms and their optical properties was investigated by PXRD, HRTEM, FT-IR, and photoluminescence. A conventional synthetic approach to prepare PbS nano particles via solvothermal method [17]. Synthesis of isotropic PbS nano particles from the single source precursor highly coordinate dithiocarbamate has been reported [18]. From these attempts, we have been focused to syntheses of PbS. Hence in this article we report the large scale PbS nano particles with high quality were successively synthesized by solvothermal process from lead(II) dithiocarbamate $[Pb(pndtc)_2]$ and its subsequent use as single source precursor. From



this work material morphology and nature of PbSnano particles has been explored. The obtained *nanolead(II)sulfide* was investigated by PXRD, HRSEM,EDAX and IR analysis.

II. EXPERIMENTAL



All the reagents and solvents employed were commercially available analytical grade materials and were used as supplied without further

purification. N-Phenyl-1-Naphthylamine are supplied by Sigma Alrich. IR spectra were recorded on an Avatar Nicolet FT-IR spectrophotometer [Range 4000 - 400 cm^{-1}] as KBr pellets. Electronic spectra were recorded in CH_2Cl_2 on a Hitachi U-2001 double beam spectrometer. ^1H , ^{13}C NMR spectra were recorded on a Bruker AMX-400 spectrometer at room temperature using CDCl_3 as solvent. Scanning electron micrographs of the sample are recorded with JOEL JSM-5610 v microscopes.

II.1 Preparation of Bis (n-phenyl-1-naphthyl)dithiocarbamate

lead(II); $[\text{Pb}(\text{pndtc})_2]$

The compound $[\text{Pb}(\text{pndtc})_2]$ was prepared by mixing N-phenyl-1-naphthylamine (4 mmol, 0.60 mL) and carbon disulphide (4 mmol, 0.24 mL) in ethanol under ice cold condition (5°C). To the yellow dithiocarbamic acid solution, aqueous solution of $\text{Pb}(\text{NO}_3)_2$ (2 mmol, 0.660 g) was added with constant stirring. A white solid separated from the solution, which was filtered, washed with alcohol and was then dried in air. (Yield: 70%, dec. 186°C , anal. calc. for $\text{C}_{34}\text{H}_{24}\text{N}_2\text{PbS}_4$ (796.0): Pb, 26.0; C, 51.3; H, 3.0; N 3.5%; found: Pb, 26.1; C, 51.9 H 3.6 N 3.9



II.2 Synthesis of PbS nanoparticles by solvothermal decomposition method using $[\text{Pb}(\text{pndtc})_2]$ as a single source precursor;

A mixture of N-phenyl-1-naphthylamine dithiocarbamate (1 g) as a clear solution in chloroform (100 mL) was heated with diethylenetriamine (2 mL) at 80°C . The black nanoPbS was obtained as a suspension. The precipitate was filtered and washed with ether, chloroform and the nanoparticles were collected and dried.

III. RESULTS AND DISCUSSION

III.1 Spectral studies

III.1.1 Infrared spectrum

Infrared spectra of the complex is shown in Fig.1 Some important spectral bands are presented in Table1. The spectrum show two characteristic absorptions due to $\nu_{\text{C-N}}$ and $\nu_{\text{C-S}}$ vibrational modes. The $\nu_{\text{C-N}}$ has been used as a measure of the contribution of the thioureide form to the structure of dithiocarbamate. A strong band around 1499 cm^{-1} is observed in all the complexes due to $\nu_{\text{C-N}}$ stretching and the band around 1000 cm^{-1} is due to $\nu_{\text{C-S}}$ stretching in the complexes. The phenyl ring C-H out of plane vibrations appear in the region: $600-736 \text{ cm}^{-1}$. The $\nu_{\text{C-H}}$ aliphatic stretching appears around 2950 cm^{-1} in the complex[19]

Table 1 Infrared spectral data (cm^{-1})

Complex	$\nu_{\text{C-N}}$ (thioureide)	$\nu_{\text{C-S}}$	Aromatic $\nu_{\text{C-H}}$	Aliphatic
$[\text{Pb}(\text{pndtc})_2]$	1499	1097	3013-3074	2852 2914




Fig 1 IR spectrum of [Pb(pndtc)₂]

III.1.2 Electronic spectrum

Electronic spectrum of the complex is shown in **Fig 2** and the corresponding λ_{max} values are presented in **Table 2**. The parent lead dithiocarbamate complexes are colourless, The electronic spectra of the parent complex show charge transfer only. The ligand transitions of the dithiocarbamates are observed below 350 nm. The charge transfer transition in [Pb(pndtc)₂] are observed at 435 nm[20]

Table 2 Electronic spectral data

Complex	λ_{max} (nm)
[Pb(pndtc) ₂]	435




Fig 2 Electronic spectrum of [Pb(pndtc)₂]

III 1.3 NMR SPECTRUM.

NMR spectral data of the synthesized compound is given along with the splitting patterns.

III.1.3.1 ¹H NMR spectrum

¹H NMR spectra of the complex is shown in **Fig 3** and the chemical shifts is given in **Table.3** ¹H NMR spectra of compound show the phenyl CH₂ proton signals at, 5.20 ppm, For the complex the aromatic protons resonate in the region 7.28-7.34 ppm... The equatorial proton attached to β and γ -carbons appear in the region of 1.71-2.03 ppm. The signals around 1.57 ppm are assigned to the δ -protons[21].




Fig 3 ¹H NMR spectrum of [Pb(pndtc)₂]

Complex	Phenyl ring protons	α -CH	β -CH -	γ -CH ₂	δ -CH ₂
[Pb(pndtc) ₂]	7.28-7.34	5.04	1.71-2.03	—	1.57

Table 3 ¹H NMR spectral data (ppm)

III.1.3.2 ¹³C NMR spectrum

¹³C NMR spectrum is shown in **Fig. 4** and the chemical shifts is given in **Table.4**. The most important chemical shifts of thioureide carbons (S₂¹³CN) are observed at 206.6, The mesomeric shift of electron density from dithiocarbamate moiety towards the metal

centre contributes to the upfield shift from the normal chemical shift of $[\text{Ni}(\text{dte})_2]$ complexes (206-210 ppm) [22]. The observation is supported by the higher $\nu_{(\text{N}-\text{C})}$ values observed (in IR) for complexes (2) and (3) in the present study. The common spin-lattice relaxation mechanism for ^{13}C results from dipole – dipole interaction with directly attached protons. Thus, non-protonated carbon atoms have longer T_1 relaxation times, which results in less intense signals, and this phenomenon is clearly observed for thioureide (N^{13}CS_2) and NCS^- carbon signals, which are of very low in intensity. From the ^{13}C NMR spectra of the complex the chemical shift of the carbon atom of the NCS_2 moiety can be correlated to the extent of π -bonding in NCS_2 fragment [22]. In the IR spectra, $\nu_{\text{C}-\text{N}}$ (thioureide) vibration is usually observed at 1500 cm^{-1} for dialkyldithiocarbamates and 1450 cm^{-1} for phenyl substituted dithiocarbamates. The normal valence state transition metal dithiocarbamates have NCS_2 (thioureide) signal above 202 ppm and the main group metal dithiocarbamates have the NCS_2 signals below 202 ppm. Generally, higher $\nu_{\text{C}-\text{N}}$ (thioureide) correlates with lower NCS_2 chemical shifts $\delta(\text{N} - ^{13}\text{CS}_2)$. Deprotonation of secondary amine by the addition of CS_2 is the first step in the preparation of dithiocarbamate complexes and this deprotonation leads to high $\text{C}=\text{N}$ bond order which results in a higher value $\nu_{\text{C}-\text{N}}$ and a low $\delta(\text{N}^{13}\text{CS}_2)$ values. Complex shows $\nu_{\text{C}-\text{N}}$ band at 1499 cm^{-1} and the NCS_2 signal is observed at 206.6 ppm. In compound naphthalene ring carbons appears at the range of 127.9 -135.1 ppm[23].

Complex	Phenyl ring	N^{13}CS_2
$[\text{Pb}(\text{pndtc})_2]$	127.9-135.1	206.6

Table 4 ^{13}C NMR spectral data (ppm)




Fig.4 ^{13}C NMR spectra of $[\text{Pb}(\text{pndtc})_2]$

III.1.3.3 Powder XRD measurement

Powder XRD pattern at room temperature is shown in **Fig. 5**. All the diffraction peaks in the XRD can be indexed to the pure PbS. The peaks correspond to (111), (200), (220), (311), (222), (400), (331) (420) and (422) which are in good agreement with the JCPDS-pattern (JCPDS File No.: 05-0592) for PbS [24]. All the diffraction peaks showed pure cubic phase of PbS. The highest peak intensity indicates the grains are preferentially oriented along (111) direction. Broadened signals indicate diminished dimensions of the particles. Average crystal diameter of the nano PbS are estimated to be 21 nm by Debye-Scherrer formula from the XRD pattern [25].




Fig.5 PXRD of $[\text{Pb}(\text{pndtc})_2]$

III 1.3.4 IR SPECTRUM

The infrared spectrum of nano lead(II) sulphide is shown in **Fig 6**. In the spectrum the broad band appeared in the range $2883\text{--}2821\text{ cm}^{-1}$ is assigned to O-H bending vibration in PbS. It indicates PbS absorbs moisture. The peaks observed at

626,1047,1384 cm^{-1} is assigned to hetero polar diatomic molecules of PbS.




Fig.6 FT-IR spectrum of nano PbS

III 1.3.5 SEM-EDX analysis

Fig 7 is a scanning electron micrograph of nano PbS and **Fig 8** shows a typical EDX pattern of PbS nano particles

The elemental composition of PbS nano particles determined using SEM – energy dispersive (SEM) spectroscopy by performing the spot measurement on particles. The major peaks are due to the presence of Pb along with sulphur. The elemental ratio of Pb to S in PbS nano particles is 58.6 : 41.4




Fig.7 SEM IMAGE OF PbS




Fig 8 EDX pattern of PbS nano particles

IV. CONCLUSION

I demonstrated that solvothermal method can be used to prepare a good quality nano PbS from dithiocarbamate as precursor. This paper presents production of PbS nano particles via solvothermal decomposition of $[\text{Pb}(\text{pndtc})_2]$ at 80°C . The nano particles have regular shape and high purity showed by PXRD of the sample. EDAX pattern of nano PbS showed major peaks due to the presence of Pb along with sulphur in the ratio of 58.6 : 41.4

V. REFERENCES

- [1] Bessergenev. V. G, Pereira R. J. F. , Botelho do Rego A. M. (2007) Thin films and oxides of 3d metals prepared from complex precursor by CVD *Surface & Coatings technology*, 21-23,pp (9141-9145)
- [2] 'Brien P. O, ParkJ. H, Waters J.(2003) A Single source approach to deposition of nickel sulphide thin film by LP-MOCVD *Thin solid films* , 431-432 , pp(502-505)
- [3] Malik M. A, Brien P. O'(2005) Organometallic and mettalo- organic precursor for nano particles precursor chemistry of advance materials *Organomet. Chem.* 9, pp (173-204)
- [4] BajiaS. C, Mishra A.(2011) Synthesis and spctroscopic characterisation of bis (N-alkyldithiocarbamato) nickel(II) complexes;Crystal structure of $[\text{Ni}(\text{S}_2\text{CNH}(\text{i-pr})_2)(\text{i-pr})_2]$ *J. Coord. Chem.*, 64, pp(2727-2734)
- [5] Nomura R. , Murai T , ToyasakiT andMatsuda H. (1995) Single source MOVPE growth of zinc sulphide thin films using zinc



dithiocarbamate complexes Thin solid films
271,1-2, pp(4-7)

[6] Pike R. D., Cui H., Kershaw R.,
Dwight K., Wold A., Blanton T. N., Wernberg A.
A. and Gysling H. J. (1993) Preparation of zinc
sulphide thin films by ultrasonic spray
pyrolysis from bis(diethyldithiocarbamate)zinc
(II) Thin solid films, 224, pp(221-226)

[7] Fainer. N. I., Kosinova M. L.,
Rumyantsev Y. M., Salman E. G. and
Kuznetsov F. A. (1996) Growth of PbS and CdS
thin films by low pressure using
dithiocarbamates, *Thin solid films*, 280,
pp(16-19)

[8] Trindade T. and'Brien P. O. (1997)
Lead(II) dithiocarbamate complexes as
precursor for LP-MOCVD of lead
sulphide *Chem. Vapor deposit.*, 3(2) pp(75-77)

[9] M. J. Almond, H. Redman and D. A. Rice
(2000) The growth of thin layers of the transition
metal sulphides Cr_2S_3 , $\alpha\text{-MnS}$ and FeS by
Chemical vapour deposition *J. Mater. Chem.*,
10, pp(2842-2846)

[10] Nomura R., Seki Y., Konishi K. and
Matsuda H. (1992) Copper - Indium Sulphide
thin films by single -source OMCVD : *Appl.*
Organomet. Chem., 6, (685-691)

[11] Xie R. C., Shang J. K. (2007) Morphological
Control in solvothermal synthesis of titanium
oxide *J. of Materials Science*, 42 (16) (6583-
6589).

[12] Choucair. M., Thordarson. P.; Stride
J. A. (2008) Gram-scale production of graphene
based on solvothermal synthesis and sonication
Nature Nano technology, 4 (1) (30-33)

[13] Hu. G., Cheng. M., Ma. D., Liu L.,
(2002) Direct synthesis of uniform hollow
carbon spheres by a self assembly template
approach *Carbon*, 40 (1948-1949)

[14] Li. J., Chen, Z., Wang R. J., and Proserpio.
D. M. (1999) Low temperature route towards
new materials: solvothermal synthesis of metal
chalcogenides in ethylene diamine
Coordination Chemistry Reviews, 190, pp
(707-735)

[15] Li. F. W. G., Zhang Z. (2005) Synthesis of
High Quality CdS Nanorods by Solvothermal
Process and their Photoluminescence *J. of*
nanoparticle research, 7(6), (685-689).

[16] Xu L., Zhang W., Ding, Y., Yu. W., Xing, J., Li.
F., Qian Y. (2004) Shape-controlled synthesis of
PbS microcrystals in large yields via a
solvothermal process *J. Crystal growth*, 273(1)
pp (213-219)

[17] Karim M. R., Akhtaruzzaman, M. D., Ashrafuz
z M., Badruzzaman M. D. (2014), A conventional
synthesis approach to prepare lead sulfide
(PbS) nanoparticles via solvothermal method
Chalcogenide letters, 11(10) 531-539

[18] Mondel G., Santra. A., Seok S., Bera P.
Synthesis of isotropic PbS nano particles from
single precursor, highly coordinate lead
complex of S- methyl dithiocarbamates
[$\text{Pb}\{\text{S}=\text{C}(\text{SCH}_3)\text{NHNH}_2\}\text{NO}_3\}_2$ *J. Nano*
science. (2014), 4, 35

[19] Summers S. P., Abboud K. A., Farrah S. R. and
Palenik G. J. (1994) Synthesis and structure of
bismuth(III) complexes with nitrotri-acetic acid
ethylene diamine tetra acetic acid and diethylene
triamine penta acetic acid *Inorg. Chem.* 33,
pp(88-92).

[20] Reynolds J. E. F. (Ed.), *Martindale, the Extra*
Pharmacopoeia, 28th edition., The
Pharmaceutical Press, London (1982)
pp(xxx+2025)

[21] Hanley D. M. and Ferguson G. (1968) The
stereochemistry of some organic derivatives of
Group VB elements. The crystal and molecular
structure of triphenylbismuth dichloride *J. Chem.*
Soc. A (2539-2543).

[22] Van Gaal H. L. M., Diesveld J. W., Pijpers F.
W., Van Der Linden J. G. M. (1979) Carbon ¹³
NMR spectra of dithiocarbamate chemical shift,
carbon -nitrogen stretching vibration frequencies
and pi bonding in the NCS_2 fragment *Inorg.*
Chem. 18(11), pp(3251-3260).

[23] Basrton D. H. R., Charpiot B., Dau E. T. H.,
Motherwell W. B., Pascard C. and Pichon C. (1948)
Helv. Chim. Acta, 67, pp(586)

[24]. Shoukry A. F., Shuaib N. M. and Ajadi A. A.
(2017) *JCPDS* File
No.: 05-0592 *J. Expl. Nano*
Science, 13(1), pp(1-11)

[25] Klug H. and Alexander L. (1962) *X-Ray*
Diffraction Procedures polycrystalline and
amorphous materials Wiley, New York, pp
(125-178)

IJEAST

INTERNATIONAL JOURNAL
OF ENGINEERING APPLIED SCIENCE
AND TECHNOLOGY

ABOUT IJEAST

International Journal of Engineering Applied Science and Technology (IJEAST) is a peer-reviewed, open access journal that publishes high-quality research papers in the field of Engineering, Applied Science and Technology.

IJEAST aims to provide a platform for researchers, academicians, and professionals to share their innovative ideas, research findings, and practical experiences with the global scientific community.

FOCUS AREAS

- Engineering
- Applied Science
- Technology
- Innovation & Development
- Interdisciplinary Studies



PEER REVIEWED

All submissions are rigorously peer reviewed to ensure quality.



OPEN ACCESS

Free and unrestricted access to research for all.



GLOBAL REACH

Connecting researchers and professionals worldwide.



TIMELY PUBLICATION

We ensure a swift and efficient publication process.



For more information, visit our website

www.ijeast.com



INTERNATIONAL JOURNAL

OF ENGINEERING APPLIED SCIENCE
AND TECHNOLOGY



editor@ijeast.com



www.ijeast.com



India



2455-2143